

Flinken Finishing Coat

Product Introduction

FLINKEN® Finishing Coat premix mortar is made from Ordinary Portland Cement(OPC) and super fine calcium carbonate with suitable methyl cellulose for excellent smooth surface and workability.



Mixing Guide

1. Mix one bag (25kgs) of FINISHING COAT with approximately 8-9 litres of clean water.
2. Mix continuously 3-5 minutes until a uniform paste is achieved and ensure the mix is from lumps.
3. Placing should be completed within 30 minutes after start of mixing.

Product Specification

Brand	FLINKEN
Type	GP- General purpose rendering and plastering mortar for internal and external use
Rating	Excellent Workability, Define, Durable
Dry Bulk Density	1320 - 1360 kg/m ³
Compressive Strength	Categories CS IV ≥ 6.0 N/mm ²
Adhesion	0.5 N/mm ²
Fracture Pattern	B Cohesive Fracture
Capillary Water Absorption	Categories W0
Water Vapour Permeability	2.0 μ
Workable Life	60 minutes
Air Content	17% - 17.5%
Coverage Area	0.8 - 1.0 m ² per kg
Shelf Life	6 months *If stored in Tdry conditions in the original and unopened bags.

Sibu (HQ) : No.18, Lorong Sukun 28, Lot 1168, Upper Lanang Industrial Estate, 96000 Sibu, Sarawak, Malaysia. Tel : 084-210600, 210700 Fax: 084-210900

Bintulu Branch : Lot 695, Blok 31, Kemena Land Distrit, 97000 Bintulu, Sarawak, Malaysia.

Tel : 086-335571 Fax: 086-335139

Kuching Branch : No.66, Jalan Semangat, Bintawa Industrial Estate, 93450 Kuching, Sarawak, Malaysia.

Tel : 082-332200 ,330099 Fax: 082-331177